

GP COAT 131

AROMATIC POLYURETHANE TOPCOAT

Description

Two component air drying aromatic polyurethane finish coating

Recommended Use

It is recommended as topcoat for Original Equipment Machines, Hygienic, Maintenance painting where mild chemical resistance along with good abrasion resistance and decorative finish are required. Sometimes it is recommended as undercoat of finish coats application for economic benefits.

Physical Data

COLOUR	: Assorted shades
FINISH	: Glossy /Semi glossy /Matt
SOLIDS BY VOLUME	: $40 \pm 3\%$ (Depends on shade)
THEORETICAL SPREADING RATE	: 13.33 sq.mt /lit at recommended DFT of 30μ
FLASH POINT	: Base : Above 23°C Hardener : Above 30°C
DRYING CHARACTERISTICS (At 30°C and 65% Relative humidity)	: SURFACE DRY : 20 - 30 minutes HARD DRY : Overnight FULL CURE : 7 days
SHELF LIFE	: BASE : 6 months HARDENER : 6 months

Surface Preparation

This being a Topcoat, which is applied over underneath primer or intermediate coats, the surface should be free from oil, moisture, dust and dirt. Aged coatings should be roughened by emery paper grade 400 /600 followed by solvent wipe for better bonding.

Application Data

MIXING RATIO	: Base : Hardener (As per our recommendation)
APPLICATION	: By Brush /By Conventional spray /By Airless Spray
THINNER	: Type 001
POT LIFE	: 3 hours min at 30°C
RECOMMENDED DFT	: $30\text{-}40\mu$.
OVERCOATING INTERVAL	: MIN : 8 hours MAX :24 hours
COMPATIBILITY	: Can be applied over Epoxy and Polyurethane primers, intermediate coats and topcoats.

Application Method

Stir the Base part thoroughly. Mix the base and hardener as per our recommended ratio, by volume. Stir the mix gently to attain homogeneity. Add Thinner Type 001 into the mix, if required, depending on application method, and stir gently for few minutes. Allow the mixture to stand still (maturation) for about 10minutes to initiate the reaction. Strain the paint through Nylon filter cloth 400 mesh size and apply uniformly over the surface. All equipments used for above should be properly clean.



Perfection in
Protection

ISO 9001
ISO 14001

Application: By Brush /By Conventional Spray /By Airless Spray

Generally no thinner is required for Brush application, however under adverse environmental conditions about 5% of thinner, by volume, can be added. Apply evenly in crossed manner and ensure the uniformity. Use quality brushes for paint application

For Conventional Spray application :

Thinner : Type 001

Addition : 5 - 15%

Nozzle Orifice : 1.2 - 1.4 mm

Nozzle Pressure : 40-70 p.s.i.

For Airless Spray application :

Thinner : Type 001

Addition : Max 5%, if required.

Nozzle Orifice : 0.28 mm

Nozzle Pressure : 1400-1800 p.s.i.

Additional Information

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following section of Grand Polycoats' Data manual

- Guide to Product Data Sheets
- Surface Preparation Details
- Paint Application Details
- MSDS

Notes

1. Do not apply paint when temperature falls below 10°C or rises above 50°C and when Relative Humidity is above 85%. Do not apply during rain, fog, or mist. Surface temperature must always be minimum of 3°C above Dew point.
2. Brushes and spray equipment should be cleaned with GP's recommended thinner otherwise equipment is liable to be damaged.
3. Volume Solids will vary depending on shades. Products with different volume solids are also available on request.
4. DFT variation can be obtained by change in application method / thinning ratio. Contact Grand Polycoats' representative for further assistance.
5. Shelf life indicated is minimum for this Product in sealed conditions and it is subject to re-inspection thereafter. Individual component is required to be stored in cool, dry and covered condition, away from heat and ignition.

Health & Safety

This is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes.

Limitation of Liability

To the best of our knowledge, the technical data in our literature are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. We make no other warranty or guarantee of any kind, express or implied, including merchantability and fitness for particular purpose. Liability, if any, is limited to replacement of the product or refund of the purchased price. Labour or cost of labour and other consequential damages are hereby excluded.

Grand Polycoats Co.Pvt.Ltd. 204, Siddharth Complex, R.C. Dutt Road, Vadodara - 390007, (Gujarat) India.

Tel.: +91-265-3064200 / 3064201 Fax: +91-265-2337022

E-mail: marketing@grandpolycoats.com Website: www.grandpolycoats.com

R : 01 / 06: 08 This supersedes all earlier versions of this product data sheet.



Perfection in
Protection

ISO 9001
ISO 14001